

<b>Product Name (Description)</b>	LDPE TRANSPARENT PACKAGING
<b>Compound</b>	100 % Virgin Petkim grade LDPE
<b>Biological Specs</b>	<b>E.Koli</b> Mustn't be exist (kob/g) Analyse Method: ISO 18593 <b>S.Aureus</b> ..... < 25 pcs kob/g Analyse Method: ISO 18593 / BAM
<b>Raw Material Specification</b>	<b>Melting Point (DSC)*</b> (ASTM E-794): 110 °C <b>Relentness Point*</b> (ASTM D-1525): 92-98 °C <b>Elongation At Break*</b> (ASTM D-638): 600-640 % <b>Tensile Strength At Yield**</b> (ASTM D-638): 85-95 kg/cm <sup>2</sup> <b>Tensile Strength At Break*</b> (ASTM D-638): 140-190 kg/cm <sup>2</sup> <b>Density, 23 °C *</b> (ASTM D-1505): 0.910-0.923) gr/cm <sup>3</sup>
<b>Chemical Properties</b>	<b>Overall Migration (Referans Method TS EN 1186/1-15 )</b> <b>Fatty Food</b> , Food Simulant D1 and D2, <b>Aqueous Food</b> , Food Simulant A, <b>Asidic Food</b> , Food Simulant B. <b>Requirement: 10 mg/dm<sup>2</sup></b> <b>IR Spectrum:</b> (Method FT-IR) <b>Analysis Result:</b> Polyethylene (PE)
<b>Shelf Life</b>	2 years
<b>Storage Conditions</b>	It should be stored in a place moisture-free, odor and no sunlight, dry and stored in a cool place.
<b>Packaging</b>	In PE bags or corrugated boxes.
<b>Distribution and Transport Conditions</b>	<ol style="list-style-type: none"><li>1. It is carried by clean and odorless trucks.</li><li>2. Keep away from direct sunshine.</li><li>3. Store it in a dry place.</li><li>4. Do not stow.</li><li>5. Warehouse's heat should be min: 4 °C / max: 40 °C.</li></ol>
<b>Warnings On Stickers</b>	Store in a dry place
<b>Usage</b>	It's for food, pharmaceutical, textile, automotive and cosmetic sectors. Usage heats are between -4 °C +60 °C
<b>Allergens</b>	No
<b>Consumer Groups</b>	General

\*External Source Measurements

Prepered By:  
Ramazan DEVELİ